



ELECTRICAL
MECHANICAL
INSULATION

GANUSA
EMI

Self Amalgamating Tape

CTB-15




CTB-15

Ethylene propylene rubber based
Self Amalgamating Tape designed for
the Communications industry

Features

- Provides protection where heat/flame is prohibited
- Covers any shape including high transition areas and elbows
- Clean strippable
- Layers meld together to form a boot that provides complete environmental protection and insulation
- U.V. and ozone resistant



Technical Data

Physical

Property	Test Method	Typical Performance
Thickness	ASTM D4325	0.03 in (0.762 mm)
Tensile Strength	ASTM D4325	350 psi (2 MPa)
Elongation	ASTM D4325	750%
Fusion	ASTM D4325	5/64 inch (2mm) max
Heat Resistance	ASTM D4325	130°C
Continuous Operating Temp	ASTM D4388	90°C
Emergency Overload	ASTM D4388	130°C

Chemical

UV Resistance	ASTM D4325	Pass
Ozone Resistance	ASTM D4325	Pass
Water Absorption	ASTM D570	0.06 %

Dimensions

ORDER REF. NO.	WIDTH		THICKNESS		ROLL LENGTH	
	mm	IN	mm	IN	m	FT
CTB-15	38.1	1.5	0.76	0.03	4.57	15

Ordering

To Order Specify:

CTB-15

Standard Colors (CC)

Order Code	Color
BK	BLACK

CANUSA-EMI

There's no end to what we cover

CANUSA-EMI is a global company providing electrical and mechanical insulation solutions for a variety of industries and applications. Starting from products created by extensive developmental research at Shaw Industries (incorporated 1955), CANUSA-EMI is a recognized world leader in the provisioning of high quality heat shrink products.

EUROPE

CANUSA SYSTEMS LIMITED

Bergstrand House

Broadley Industrial Park

Roborough Plymouth, U.K. PL6 7EZ

Tel: (01752) 209880

Fax: (01752) 209850

U.S.A.

CANUSA - EMI

P.O. Box 498830

Cincinnati, Ohio 45249

Tel: 1-800-422-6872

Tel: (513) 683-7800

Fax: (513) 683-7809

CANADA/INTERNATIONAL

CANUSA - EMI

25 Bethridge Road

Toronto, Ontario M9W 1M7

Tel: 1-800-845-6808

Tel: (416) 743-7111

Fax: (416) 743-7199

WORLDWIDE WEB: www.canusa-emi.com

All information contained in this leaflet is believed to be reliable. We advise however that customers should separately evaluate the suitability of our products for their particular application. CANUSA-EMI and Shaw Industries give no guarantees in respect of the accuracy or sufficiency of the information presented and disclaim any liability regarding its use. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. In no instance will we be liable for any eventual, indirect, or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product.